



**SILICONE**

## 18 **SILICONE DYE-BLOCK / ST370**

**TYPES OF MACHINES/EQUIPMENT USED:** Vinyl cutter and heat press

**MATERIALS USED:** AquaTru™ Dye-Block™ from Stahls'

**PROCESSES USED:** 12-second heating time at 275°F, medium pressure and hot peel

**ADDITIONAL NOTES:** Available in cuttable sheets



**SILICONE**

### **DESIGN INTENT:**

Excellent for heat-applied transfers on sublimated and synthetic garments without dye migration. These are highly flexible, stretching with the fabric.

### **TRADITIONAL TECHNIQUES TREND IS BASED ON:**



**DISCLAIMER:** The information contained on this card is for general reference purposes only. SanMar does not endorse or recommend any decoration process or embellishment technique. Decoration success is based on a variety of factors including the quality of the artwork, equipment, raw materials used and operator experience. All technical questions about the decoration process you intend to use should be directed to your trusted decorator or equipment and raw materials supplier.